

Corroless RF16

High Build Reinforced Gloss Topcoat

 Issue Date: June 2020
 Code: 2004
 Page 1 of 2

Product Description	A single pack general purpose, glass reinforced high build alkyd topcoat				
Features & Use	<ul style="list-style-type: none"> • Contains glass flake for improved impermeability and abrasion resistance • High build – reduces application costs and saves time • Good application properties • Fast drying compared to other high build alkyds, to help reduce the possibility of dust contamination shortly after application • Applications include pipes, mechanical equipment, bridges, fire escapes, storage tank externals and structural steel 				
Approvals/ Certification	<ul style="list-style-type: none"> • Sold on track record and customer recommendation 				
Finish	Gloss				
Volume Solids	42% ± 2%				
VOC Content	500 g/litre (average)				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Typical	50 µm	119 µm	8.4 m ² /litre	
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated				
Drying Times	Applied to 50 microns DFT	+10°C	+18°C	+30°C	
	Dust Free		2 hr	1½ hrs	45 mins
	Hard Dry		8 hr	6 hr	3 hr
	Overcoating	Minimum	24 hr	16 hr	10 hr
		Maximum	Indefinite	Indefinite	Indefinite
	Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation				
Colours	Available in a wide range of colours				
Mix Ratio	Single Pack				
Pot Life	Not applicable				
SG	0.9-1.1 depending on colour				
Storage Conditions	Store in dry, cool conditions and protect from frost				
Shelf Life	Minimum 24 months if stored as above in unopened containers				
Flash Point	21-32°C				

Corroless RF16

Issue Date: June 2020
Page 2 of 2

Surface Preparation	<ul style="list-style-type: none"> If required due to obvious dirt/grease contamination or suspected salt or chemical contamination, clean all surfaces with a water-soluble degreaser, wash down with clean fresh water and allow to dry before application This is a finish coat and should be applied over a Corroless Primer Recommended Primers: Corroless S, SHB, and QDR 														
Mixing	Stir thoroughly before use														
Thinner / Cleaner	Corroless Thinners No.3 (Spray) or No.2 (Brush). Solvent Gun Wash may be used for cleaning only														
Application Conditions	Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Paint temperature should ideally be at a minimum of 15°C.														
Application Methods	<table border="1"> <thead> <tr> <th data-bbox="416 875 687 943">Method</th> <th data-bbox="692 875 935 943">Airless Spray</th> <th data-bbox="940 875 1182 943">Conventional Spray</th> <th data-bbox="1187 875 1334 943">Brush</th> <th data-bbox="1339 875 1471 943">Roller</th> </tr> </thead> <tbody> <tr> <td data-bbox="416 949 687 1010"></td> <td data-bbox="692 949 935 1010">Yes</td> <td data-bbox="940 949 1182 1010">Yes-Thinning required</td> <td data-bbox="1187 949 1334 1010">Yes</td> <td data-bbox="1339 949 1471 1010">Yes</td> </tr> </tbody> </table>					Method	Airless Spray	Conventional Spray	Brush	Roller		Yes	Yes-Thinning required	Yes	Yes
	Method	Airless Spray	Conventional Spray	Brush	Roller										
	Yes	Yes-Thinning required	Yes	Yes											
<ul style="list-style-type: none"> Airless spray: output fluid pressure 1800-2500 psi, tip size 11-19 thou Fan Angle 30-50°C. For detailed advice contact Corroless Conventional Spray: An addition of up to 10% Corroless Thinners No.3 will be required Brush: apply unthinned, lay on, do not over brush When rolling, use a short nap lamb's wool roller and a maximum addition of 5% Corroless Thinners No.2. Lay off with a brush to complete the finish 															
Product Notes	<ul style="list-style-type: none"> Application Temperature: Range 5°C-30°C Stripe Coating: Stripe coat all edges, nuts and bolts, welds etc. Overcoating: Overcoat with itself. If overcoating time is exceeded and contamination has occurred, clean using a detergent solution/fresh water and allow to dry before continuing No maximum overcoat time, but if contamination has occurred, clean using a detergent solution/fresh water and allow to dry before continuing 														
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.														

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.