

Energy Solutions Impregnating Resins

Product Overview Voltabas, Voltahyd,
Voltatex® (Additives, Thinners, Cleaners)



Energy Solutions - Impregnating Resins

Voltabas, Voltahyd

Product	Key Characteristics	Thermal Class (IEC 60085)	UL-Recognition	Viscosity @ 25°C DIN 53019 [mPas]	Gel Time [min]	Emissions DIN EN 60455-3-5 [%]	Typical Curing Time
---------	---------------------	------------------------------	----------------	---	-------------------	--------------------------------------	---------------------

Voltabas 0302	Modified unsaturated polyester resin, single component, VOC-free	180°C (H)	✓	1000-1700	20.0-40.0 @ 100°C	≈0.8	2h @ 150°C
Voltabas 0303	Modified unsaturated polyester resin, single component, VOC-free	180°C (H)	✓	300-500	20.0-40.0 @ 100°C	≈0.6	1-2h @ 150°C
Voltabas 0307	Unsaturated polyester resin, epoxy-modified, single component, VOC-free	180°C (H)	(✓)	300-500	20.0-40.0 @ 100°C	≈0.8	2h @ 150°C
Voltabas 0307 TX	Unsaturated polyester resin, epoxy-modified, thixotropic single component, VOC-free	180°C (H)	(✓)	300-500	20.0-40.0 @ 100°C	≈0.9	2h @ 150°C
Voltabas 0310 M	Unsaturated polyesterimide resin, single component, VOC-free	180°C (H)	✗	1000-2000	8.0-12.0 @ 90°C	≈0.6	15 min @ 150°C

Product	Key Characteristics	Thermal Class (IEC 60085)	UL-Recognition	Viscosity @ 25°C DIN 53019 [mPas]	Flow Time DIN 53211 [s]	Typical Curing Time tack free / ready to assembly
---------	---------------------	------------------------------	----------------	---	-------------------------------	---

Finishing Varnish/ Topcoat

Voltahyd 2220 red	Modified hybrid resin, single component, water based, low emission red pigmented	(✓)	✗	200-450	70-150 @ 23°C (4mm)	45-60 min @ 25°C/ 24-36 h @ 25°C
Voltahyd 2220 grey	Modified hybrid resin, single component, water based, low emission grey pigmented	(✓)	✗	200-450	80-160 @ 23°C (4mm)	45 min @ 25°C/ 24 h @ 25°C

Conductive Varnish

Voltahyd 2300	Modified alkyd resin, waterborne, single component, specially pigmented	✗	✗	300-1000	-	NA/ 2-5 min @ 140°C
----------------------	---	---	---	----------	---	------------------------

- ✓ = listed
- (✓) = pending
- ✗ = not listed

Shelf Life ≤ 25°C	Product Description	Typical Application	Dip & Bake (atmospheric)	Vacuum Process	VPI	Hot Dip-ping	Resistance Heating Process	UV-Curable	Trickle	Roll-Dip
----------------------	---------------------	---------------------	-----------------------------	----------------	-----	--------------	----------------------------	------------	---------	----------

suitable for:

12 months	Low viscosity	Low voltage stators, rotors, transformers, (wind) generators	✓	✓	✓	✓	✓	✗	✓	✓
12 months	Very low viscosity	Low voltage stators, rotors, transformers, (wind) generators	✓	✓	✓	✓	✓	✗	✓	✓
12 months	Very low viscosity, low crack tendency	Low voltage stators, rotors, transformers, (wind) generators	✓	✓	✓	✓	✓	✗	✓	✓
12 months	Low draining losses, thixotropy adjustable, very low viscosity, low crack tendency	Low voltage stators, rotors, transformers, (wind) generators	✓	✓	✓	✓	✓	✗	✗	✓
3 months	Low viscosity, high reactive, short curing time	low voltage, small rotors and stators (e.g. alternators)	✗	✗	✗	✗	✗	✗	✓	✗

Shelf Life ≤ 25°C	Product Description	Typical Application	Dip & Bake (atmospheric)	Brushing & Spraying	Roll-Dip
----------------------	---------------------	---------------------	-----------------------------	---------------------	----------

suitable for:

6 months	Quick drying, additional protection against external influences, mould resistance, tested in acc. with EN 45545-2, good adhesion to steel, galvanized substrates and aluminum	low voltage, transformers, stators, traction motors, (wind) generators	✓	✓	✗
6 months	Quick drying, additional protection against external influences, mould resistance, tested in acc. with EN 45545-2, good adhesion to steel, galvanized substrates and aluminum	low voltage, transformers, stators, traction motors	✓	✓	✗

6 months	Quick drying, provide electrical conductivity on surfaces, air or fast oven drying, good adhesion on steel, glass and e.g. PET	Corona shielding	✓	✓	✓
----------	--	------------------	---	---	---

- ✓ = recommended
- ⊗ = conditionally recommended (please consult us)
- ✗ = not recommended

Energy Solutions - Impregnating Resins

Voltatex® Cleaner, Additive

Product	Key Characteristics	Shelf Life ≤ 25°C	Flash Point	Product Description
---------	---------------------	----------------------	-------------	---------------------

Cleaning Agent

Product	Key Characteristics	Shelf Life ≤ 25°C	Flash Point	Product Description
Voltatex® T050	Propylenglycol ester, clear, transparent solvent mixture	12 months	46°C	Excellent cleaning properties for uncured residues of varnishes or resins, quick-drying surface
Voltatex® T060	Dibasic ester, clear, transparent solvent mixture	12 months	100°C	Excellent cleaning properties for uncured residues of solventborne/solventfree varnishes or resins
Water-borne Prepclean 3910 WB	Clear, transparent mixture of water and solvents	60 months	68°C	Cleaner for residues of Voltahyd series or other waterbased products, also used as preparatory cleaner

Product	Key Characteristics	Shelf Life ≤ 25°C	Product Description
---------	---------------------	----------------------	---------------------

Additive

Product	Key Characteristics	Shelf Life ≤ 25°C	Product Description
Voltatex® H140	Yellow, pasty liquid hardener solution, free of peroxides	6 months	Can be added to Impregnating Resins (based on unsaturated polyester/polyesterimide) for adjusting the reactivity
Voltatex® H151	Organic peroxide white, fine-grained powder with 50% active ingredient	6 months	Curing agent for low temperature curing 80 - 120 °C
Voltatex® A341	Organic metal compound, dark-violet liquid	90 months	Catalyst for polymerization at room temperature of impregnating resins (based on unsaturated polyester / polyesterimide) with MEK-peroxide or Voltatex® H151
Voltatex® A200	Inhibitor, dark-brown liquid	12 months	Can be added to significantly reduce reactivity or stabilizing of dipping tanks with unsaturated polyester / polyesterimide
Voltatex® A401	Polyhydroxycarboxylic acid amid, transparent to slightly brown liquid, thixotropy agent	6 months	Can be added to Voltatex® gel coats or Voltabas 0307 TX for enhancing the viscosity

Energy Solutions - Impregnating Resins

Voltatex® Thinner Product Overview

Product	Key Characteristics	Shelf Life ≤ 25°C	Flow Time DIN 53211 [s]	Viscosity DIN 53019 @25°C [mPas]	Product Description
---------	---------------------	----------------------	-------------------------------	--	---------------------

Thinner

Voltatex® T031	Unsaturated aromatic hydrocarbon, clear, transparent and specially stabilized reactive thinner	6 months	<20 @ 23°C (4mm)	≈ 0,7	Can be added to Impregnating Resins Voltatex® 4000 series to adjust the required viscosity
Voltatex® T032	Unsaturated aromatic hydrocarbon, clear, transparent and specially stabilized reactive thinner	6 months	<20 @ 23°C (4mm)	≈ 0,8	Can be added to Impregnating Resins Voltatex® 4100 series to adjust the required viscosity
Voltatex® T033	Unsaturated methacrylate ester, clear, transparent and specially stabilized reactive thinner	6 months	<20 @ 23°C (4mm)	10-14	Can be added to Impregnating Resins Voltatex® 4200 series to adjust the required viscosity
Voltatex® T034	Unsaturated acrylate ester, clear, transparent and specially stabilized reactive thinner	6 months	-	60-100	Can be added to Impregnating Resins Voltatex® 4300 series to adjust the required viscosity, monomerfree, VOC-free
Voltatex® T035	Unsaturated methacrylate ester, clear, transparent and specially stabilized reactive thinner	6 months	-	≈ 30	Can be added to Impregnating Resins Voltatex® 4300 series to adjust the required viscosity; monomerfree, VOC-free
Voltatex® T040	Water, dest.	6 months	-	≈ 1	Can be added to Voltahyd series to adjust the required viscosity, VOC-free
Voltatex® T041	Waterbased amine solution, clear, transparent thinner and stabilizer	12 months	-	≈ 1	For stabilization of dipping tanks with Voltahyd 2220
Voltatex® T042	Waterbased solution clear, transparent thinner and accelerator	6 months	-	≈ 1	Accelerator for spray applications of Voltahyd series, VOC-free



Axalta Coating Systems Germany GmbH & Co. KG
Energy Solutions
Technical Service
Christbusch 25
D-42285 Wuppertal

www.electricalinsulation.com
electricalinsulation@axalta.com



The Axalta logo, Axalta™, Axalta Coating Systems™ and all products denoted with™ or® are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta Trademarks may not be used in connection with any product or service that is not an Axalta product or service. Axalta Coating Systems 50 Applied Bank Blvd, Suite 300 Glen Mills, PA 19342 | 03/2024