

Gotalene® RS 410 Pink 23

100% Bio-based exfoliating powders for Personal Care

Article number: 7038-3

Product description

Gotalene® RS410 Pink 23 is a biodegradable* cosmetic additive based on **Polylactic Acid** powders that offers excellent cutaneous tolerance. It is specially developed for skin cleansing preparations and has natural, efficient and medium abrasive properties. **Gotalene® RS410 Pink 23** is 100% Renewably Sourced from plant sugars.

Applications

Gotalene® RS410 Pink 23 is used as an exfoliating agent for controlled scrubbing effects in soaps, gels and creams for face and body (face scrub cleanser, body scrubs, shower gel, exfoliating foot care, body butter, toothpaste, lip scrub, hair care...)

*Polylactic acids can biodegrade in 20 to 40 days in compost pile, in specific temperature (>60°C) and humidity conditions. Does not biodegrade in a conventional landfill.

Regulatory information

✓ Compliant with the European Cosmetics Regulation (EC) No 1223/2009.

✓ Contains no CMR, GMO, Glycol ether or substances of animal origin.

INCI name: POLYLACTIC ACID & may contain pigment and dyes (available upon request)

CAS numbers: 9051-89-2

Complementary information

- ✓ Shelf life: 1 year
- ✓ Storage conditions: Cool (T°<50°C) and dry place

Characteristics

General properties	Units	Methods	Typical Values / Ranges
Chemistry	/	/	POLYLACTIC ACID
Color	/	Visual	Pink
Physical form	/	/	Dry Powder
Particle size, maximum	µm	Alpine Air Jet Sieve LS200	97-100 % below 315
Particle size, mean (X50)	µm	Laser ISO 13320-1	210 – 320 (preliminary)
Melting Point	°C	Mettler DSC 822e	160-185
Specific gravity	g / cm ³	ASTM D 1505	1,25
Bulk Density	g/ml	ASTM D 1895	≥ 0.28
Melt Flow Rate	g/10min	ISO 1133 (190°C/2.16kg)	10-30
Exfoliation type	/	Sensorial	Medium

Despite the fact that Gotalene RS is formulated with biodegradable plastics, Axalta does not warrant or otherwise represent that Gotalene RS is suitable for use in rinse-off cosmetics in jurisdictions where plastic microbeads have been banned for use in such applications.

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Copyright 2018, Axalta Coating Systems, LLC and all affiliates. The Axalta logo, Axalta™, Axalta Coating Systems™ and all products denoted with ™ or ® are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta trademarks may not be used in connection with any product or service that is not an Axalta product or service.