



**Audurra™ Premium Masking foil**

**MASKING**

**Description:**

Good cutting ability and electrostatic adhesion of the Audurra™ Premium Masking Foil (Polythene light-blue transparent) accelerate the work steps and are a prerequisite for safe and accurate covering. Due to its heat resistance up to 110°C it can be used with infrared dryers. Important: No staining from residual moisture at the vehicle, no severance of paint and water.



**Available in:**

Article number	Description	Dimension
D15352434	Audurra™ Premium Masking foil	4 m x 120 m
D15366258	Audurra™ Premium Masking foil	6 m x 80 m

**Compatible with:**

Article number	Article description	Packaging unit
D15352436	Audurra mobile dispenser for foil cartons	1 piece
D15352432	Audurra Foil Cutter	1 bundle = 5 pieces



**Audurra™ Premium Masking foil**

**MASKING**

**Properties:**

Property	Value & measuring unit	Measuring method
Density	~ 1,04 g / cm <sup>3</sup>	following DIN EN 1183
Thickness	11 µm	following GPA (Thickness-profile)
Tensile Strength <i>machine direction</i>	>30 N / mm <sup>2</sup>	following ASTM D 882
Tensile Strength <i>transverse direction</i>	>20 N / mm <sup>2</sup>	following ASTM D 882
Elongation at break <i>machine direction</i>	>150 %	following ASTM D 882
Elongation at break <i>transverse direction</i>	>300 %	following ASTM D 882
Dart drop	>3,5 g/µm	following ASTM 1709-91
Dimension and Design	4 m x 120 m	

**Storage remarks:**

Storage time is 12 months from delivery date. Keep storage temperature between + 20° C / ± 10° C and the relative humidity by 30 – 90%.

Storage in closed rooms. Avoid exposure to UV-radiation.

This technical information has been given to the best of our knowledge. The above mentioned standards are average values and no granted assurance of special properties. This statement is limited to the material, in the state as it leaves the manufacturer and does not include possible modifications by conversion and/or handling after dispatch.

