

SYSTEM POSTER

SYROX™

KEINE KOMPROMISSE

S1000 UNIVERSAL POLYESTER PUTTY		2%								20 °C 15 - 20 min.
			+ BPO HARDENER PASTE RED	BPO HARDENER PASTE RED						
S2000 1K WASH PRIMER		2:1								
				S8000 THINNER				1 Spritzgang 1.3 - 1.5 mm		20 °C 10 - 15 min.
S2500 PLASTIC ADHESION PROMOTER		READY TO USE								
								1-2 Spritzgänge 1.2 - 1.3 mm		20 °C 10 - 15 min.
S3020 / 3060 SANDING SURFACER		4:1 0-10%								
LG - S3020 DG - S3060					S6020 HS ACTIVATOR FAST			1-3 Spritzgänge 1.6 - 1.9 mm		
					S6010 HS ACTIVATOR STANDARD					
					S6000 HS ACTIVATOR SLOW					60 - 65 °C 25 - 30 min.
S3020 / 3060 WET-ON-WET SURFACER		3:1+40%								
LG - S3020 DG - S3060					S6020 HS ACTIVATOR FAST			1 Spritzgang 1.3 - 1.4 mm		
					S6010 HS ACTIVATOR STANDARD					
					S6000 HS ACTIVATOR SLOW				Endablüfzeit 30 min bei 20°C	
BASECOAT		+20%								
				S940 BASECOAT THINNER				2.5 Spritzgänge 1.2 - 1.4 mm		Matt ablüften lassen
S5000 HS TOP CLEAR		2:1								
				S6030 HS ACTIVATOR VERY FAST				1.5 - 2 Spritzgänge 1.3 - 1.4 mm		
				S6020 HS ACTIVATOR FAST						60 - 65 °C 25 - 35 min.
				S6010 HS ACTIVATOR STANDARD						
				S6000 HS ACTIVATOR SLOW						
S5100 HS AIR DRY CLEAR		2:1								
				S6010 HS ACTIVATOR STANDARD				2 Spritzgänge nass-in-nass 1.3 - 1.4 mm		20 °C 40 - 50 min.

Spot Repair
 Einzelteile
 Teil-Lackierungen
 Ganz-Lackierungen
 Hohe Temperaturen