

# SYSTEM POSTER

# SYROX™

KEINE KOMPROMISSE

<b>S1000 UNIVERSAL POLYESTER PUTTY</b>		2%								20 °C 15 - 20 min.
			+ BPO HARDENER PASTE RED	BPO HARDENER PASTE RED						
<b>S2000 1K WASH PRIMER</b>		2:1								
				S8000 THINNER				1 Spritzgang 1.3 - 1.5 mm		20 °C 10 - 15 min.
<b>S2500 PLASTIC ADHESION PROMOTER</b>		READY TO USE								
								1-2 Spritzgänge 1.2 - 1.3 mm		20 °C 10 - 15 min.
<b>S3020 / 3060 SANDING SURFACER</b>		4:1 0-10%								
LG - S3020 DG - S3060					S6020 HS ACTIVATOR FAST				1-3 Spritzgänge 1.6 - 1.9 mm	
					S6010 HS ACTIVATOR STANDARD					
					S6000 HS ACTIVATOR SLOW					60 - 65 °C 25 - 30 min.
<b>S3020 / 3060 WET-ON-WET SURFACER</b>		3:1+40%								
LG - S3020 DG - S3060					S6020 HS ACTIVATOR FAST				1 Spritzgang 1.3 - 1.4 mm	
					S6010 HS ACTIVATOR STANDARD					
					S6000 HS ACTIVATOR SLOW				Endablüfzeit 30 min bei 20°C	
<b>BASECOAT</b>		+20%								
					S940 BASECOAT THINNER				2.5 Spritzgänge 1.2 - 1.4 mm	
									Matt ablüften lassen	
<b>S5000 HS TOP CLEAR</b>		2:1								
					S6030 HS ACTIVATOR VERY FAST				1.5 - 2 Spritzgänge 1.3 - 1.4 mm	
					S6020 HS ACTIVATOR FAST					
					S6010 HS ACTIVATOR STANDARD				60 - 65 °C 25 - 35 min.	
					S6000 HS ACTIVATOR SLOW					
<b>S5100 HS AIR DRY CLEAR</b>		2:1								
					S6010 HS ACTIVATOR STANDARD				2 Spritzgänge nass-in-nass 1.3 - 1.4 mm	
									20 °C 40 - 50 min.	

Spot Repair  
 Einzelteile  
 Teil-Lackierungen  
 Ganz-Lackierungen  
 Hohe Temperaturen