

SYSTEM POSTER

SYROX™

NO COMPROMISE

S1000 UNIVERSAL POLYESTER PUTTY		2%							
			+ BPO HARDENER PASTE RED		BPO HARDENER PASTE RED			 20 °C 15 - 20 mins.	 20 °C 15 - 20 mins.
S2000 1K WASH PRIMER		2:1							
					S8000 THINNER			 1 Coat 1.3 - 1.5 mm	 20 °C 10 - 15 mins.
S2500 PLASTIC ADHESION PROMOTER									
			READY TO USE					 1-2 Coats 1.2 - 1.3 mm	 20 °C 10 - 15 mins.
S3020 / 3060 SANDING SURFACER		4:1 0-10%							
LG - S3020						S6020 HS ACTIVATOR FAST		 1-3 Coats 1.6 - 1.9 mm	
DG - S3060						S6010 HS ACTIVATOR STANDARD			 60 - 65 °C 25 - 30 mins.
S3020 / 3060 WET-ON-WET SURFACER		3:1+40%							
LG - S3020						S6020 HS ACTIVATOR FAST		 1 Coat 1.3 - 1.4 mm	
DG - S3060						S6010 HS ACTIVATOR STANDARD			 Final flash off 30 mins @ 20°C
BASECOAT		+20%							
						S940 BASECOAT THINNER		 2.5 Coat 1.2 - 1.4 mm	 Untill matt
S5000 HS TOP CLEAR		2:1							
						S6030 HS ACTIVATOR VERY FAST		 1.5 - 2 Coats 1.3 - 1.4 mm	
						S6020 HS ACTIVATOR FAST			 60 - 65 °C 25 - 35 mins.
S5100 HS AIR DRY CLEAR		2:1							
						S6010 HS ACTIVATOR STANDARD		 2 Coats wet-on-wet 1.3 - 1.4 mm	 20 °C 40 - 50 mins.
S5200 HS FLEX CLEAR		2:1+5%							
						S6010 HS ACTIVATOR STANDARD		 2 Coats 2 - 5 mins. intermediate flash off 1.2 - 1.3 mm	 60 - 65 °C 15 - 20 mins.

 Spot Repairs
  Individual parts - Paintwork
  Part - Paintwork
  Complete-Paintwork
  High temperatures