



Axalta™ Bug & Tar Remover 225



GENERAL

DESCRIPTION

A solvent mixture used primarily to remove tough bug and tar residue prior to surface preparation.

The products referenced herein may not be available for sale in your market. Please consult your distributor for product availability.



MIXING

COMPONENTS

Axalta™ Bug & Tar Remover 225

MIX RATIO

Ready-to-Use

SPECIAL TIPS

- Wash vehicle and/or part with soap and water.
- Use Axalta Bug & Tar Remover 225 on remaining bug and road grim spots with a clean cloth.
- Heavily soiled areas need to be cleaned more than once.
- This product is not suitable for cleaning spray guns or tools or removing release agents from raw plastic parts.
- Continue with surface preparation and final clean the plastic substrate thoroughly with Axalta Silicone Remover 200 Slow, Axalta Silicone Remover 210 Water, or Axalta Silicone Remover 220 Low VOC.



APPLICATION

FIELD OF APPLICATION

For cleaning surfaces to remove tough bug and tar residue prior to surface preparation.

PROCEDURE

- Apply Axalta Bug & Tar Remover 225 with a spray bottle or clean cloth.
- Wipe dry with a clean cloth before Axalta Bug & Tar Remover 225 evaporates.



PHYSICAL PROPERTIES

Coating Category: Surface Preparation
 Max. VOC (AP): 347 g/l; 2.9 lbs/gal
 Avg. Gallon Weight: 1,089 g/l; 9.1 lbs/gal
 Avg. Weight % Volatiles: 100.0%
 Avg. Weight % Water: 0.0%
 Avg. Weight % Exempt Solvent: 68.2%
 Avg. Volume % Water: 0.0%
 Avg. Volume % Exempt Solvent: 56.1%

VOC REGULATED AREAS

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.



SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and SDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties.

Revised: September 2019

In the United States:
1.855.6.AXALTA
axalta.us

In Canada:
1.800.668.6945
axalta.ca

