



A-7480S™ ACRYLIC TRIM AND JAMB CLEARCOAT



GENERAL

DESCRIPTION

A 1K clearcoat in aerosol format for cosmetic repairs. It is easy to use and provides outstanding appearance.

The products referenced herein may not be sold in your market. Please consult your distributor for product availability.



MIXING

COMPONENTS

A-7480S™ Acrylic Trim and Jamb Clearcoat

MIX RATIO

Ready to use



APPLICATION

SUBSTRATES

Sanded substrates
 OEM finishes
 Cured, repainted surfaces
 Sanded primers

SURFACE PREPARATION

- For application over properly prepared basecoat.
- Mask the repair area to prevent overspray from sticking.
- Allow basecoat to dry 15-30 minutes prior to application of A-7480S™.

APPLICATION

- Primarily recommended for cosmetic repairs.
- Shake aerosol for 2 minutes to ensure contents are uniformly mixed.
- Apply 2 medium-wet coats to prepared basecoat. Flash 10-15 minutes between coats.



DRY TIMES

AIR DRY

Flash Between Coats:	10-15 minutes
Dust Free:	30 minutes at 70°F (20°C)



PHYSICAL PROPERTIES

PWMIR Category:	Clear Coating Products (CCP)
Max. VOC (AP):	519 g/L (4.3 lbs./gal)
Avg. Gallon Weight:	760 g/L (6.34 lbs./gal)
Avg. Weight % Volatiles:	87.8%
Avg. Weight % Water:	0.0%
Avg. Weight % Exempt Solvent:	19.4%
Avg. Volume % Water:	0.0%
Avg. Volume % Exempt Solvent:	18.6%
Flash Point:	See SDS



VOC REGULATED AREAS

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.

SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS/SDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Revised: April 2017

In the United States:
1.855.6.AXALTA
cromax.us

In Canada:
1.800.668.6945
cromax.ca

