

CROMAX® XP BASECOAT

DeVilbiss

Gun	Cap	Tip	Application Pressure (Psi)	Effect Coat Pressure (Psi)
Tekna® Prolite (Black)	TE 20	1.3-1.4	25-26	25-26
Tekna® Prolite (Blue)	TE 10	1.3-1.4	24-26	24-26
GPG	7E7	1.3-1.4	20-22	20-22
DV1	HVLP Plus	1.3-1.4	18-20	18-20

SATA

Gun	Cap	Tip	Application Pressure (Psi)	Effect Coat Pressure (Psi)
2000 HVLP		1.3-1.4	29	29
3000 HVLP		1.3-1.4	29	29
5000 RP		1.2-1.3	25-26	25-26
5000 HVLP		1.3-1.4	25-26	25-26
5500 RP	"O" Cap	1.2-1.3	25-26	25-26
5500 HVLP	"O" Cap	1.2-1.3	25-26	25-26
1500 Solv RP		1.3-1.4	26	26
1500 Solv HVLP		1.3-1.4	26	26

Iwata

Gun	Cap	Tip	Application Pressure (Psi)	Effect Coat Pressure (Psi)
Evo	HD	1.2-1.3	25-26	25-26
Entech	Silver	1.4	25-26	25-26
LPH-400	Silver	1.3-1.4	16	16

3M

Gun	Cap	Tip	Application Pressure (Psi)	Effect Coat Pressure (Psi)
Performance Spray Gun	HVLP	1.3	20	20



Sagola

Gun	Cap	Tip	Application Pressure (Psi)	Effect Coat Pressure (Psi)
4600	DVR Titania	1.3-1.3XL	26-27	26-27
3300GTO	Tech	1.3	26	26

Walcom

Gun	Cap	Tip	Application Pressure (Psi)	Effect Coat Pressure (Psi)
360 Carbonio	HTE-B	1.3	26-27	26-27

March 2023

1.855.6.AXALTA
cromax.us

axalta.us