



# Permacron® 1:1 Elastic Primer Surfacer 3300



## GENERAL

### DESCRIPTION

A universal 2K Primer Surfacer for all plastic parts commonly found on passenger vehicle exteriors.

This economical primer surfacer can be recoated directly with an elastic base coat. It is characterized by good adhesion, high elasticity, and easy application. Permacron® 1:1 Elastic Primer Surfacer 3300 is available in gray and black.

The products referenced herein may not be available for sale in your market. Please consult your distributor for product availability.



## MIXING

### COMPONENTS

Permacron® 1:1 Elastic Primer Surfacer 3300

### PERMACRON ELASTIC HARDENER

Permacron® Elastic Hardener 3301

### MIX RATIO

Component	Volume
3300	1
3301	1

### APPLICATION VISCOSITY

Approximately 17 – 21 seconds at 68°F/20°C, DIN 4

### POT LIFE

Approximately 8 hours at 68°F/20°C

### SPECIAL TIPS

1. Do not allow Permahyd® Plastic Cleaning Paste 7081 to dry on the surface of the plastic substrate.
2. Thoroughly clean and scuff all surfaces of the plastic part, paying special attention to all edges.
3. For hard to reach areas of the plastic part, use the application brush that is included with the Permahyd® Plastic Cleaning Paste 7081.
4. Permahyd® Plastic Cleaning Paste 7081 is designed for raw plastic and is not suitable for cleaning painted surfaces.
5. Always use a clean scuff pad.
6. Soft plastic may require a finer scuff pad.
7. Difficult to clean plastics may need to be cleaned more times, or if applicable the plastic may be baked for a minimum of 15 minutes at 140°F (60°C). Some OEM plastic bumpers do not recommend a bake cycle. Once the plastic has cooled, repeat the procedure below for preparing raw plastics beginning with step 2.
8. Plastic parts repaired with Permacron® 1:1 Elastic Primer Surfacer 3300 may not be washed with a high pressure jet within six weeks of the repair. After this period, the nozzle must be held at a distance of no less than 12 inches from the object.



**APPLICATION**

**SUBSTRATES**

All raw plastic parts commonly found on vehicle exteriors (Examples: PP, PP/EPDM, ABS, SAN, PC, PA, PUR-RIM, R-TPU, TPO, PBTP, UP-GF).

Not recommended for pre painted substrates.

**SURFACE PREPARATION**

**Primed Plastic**

Perform a solvent test to check if primer is reversible.

1. If the primer is reversible, then strip and treat as raw plastic.
2. If the primer is not reversible
  - a. Wash with soap and water, clean with Permaloid® Silicone Remover 7010 Slow, Permahyd® Silicone Remover 7085, or Permahyd® Silicone Remover 7096. Sand primer (with P500-800 when dry sanding or with P600-800 when wet sanding). Make sure to scuff all of the edges and hard to reach areas with a gray or gold scotch pad.
  - b. Re-clean with Permaloid® Silicone Remover 7010 Slow, Permahyd® Silicone Remover 7085, or Permahyd® Silicone Remover 7096.
  - c. Recoat with an elastic Permasolid® Surfacer or Sealer.

**Raw Plastic**

The substrate must be free from release agents.

1. Rinse the raw plastic part thoroughly with water and pre-clean it using Permahyd® Plastic Cleaning Paste 7081 and a clean gold scuff pad.
2. Continue to clean the raw plastic part another 2 to 3 times using new Permahyd® Plastic Cleaning Paste 7081 and a clean gold scuff pad. The supplied brush should be used with Permahyd® Plastic Cleaning Paste 7081 in hard to reach areas of the plastic part.
3. Remove all Permahyd® Plastic Cleaning Paste 7081 residue from the plastic by thoroughly rinsing with clean water.
4. Before further treatment, clean the plastic substrate thoroughly with Permaloid® Silicone Remover 7010 Slow, Permahyd® Silicone Remover 7085, or Permahyd® Silicone Remover 7096.
5. Apply Permacron® 1:1 Elastic Primer Surfacer 3300 as per below and recoat with Permacron® Base Coat Series 293/295 or Permahyd® Hi-TEC 480.

**SPRAYGUN SETUP**

HVLP	1.3-1.4mm
Approved Transfer Efficiency	1.2-1.3mm

Please refer to gun manufacturer and local legislation for proper spray pressure recommendations.

**APPLICATION**

- Apply 1.5 coats (one tack coat followed by one full coat to obtain opacity).

**RECOMMENDED FILM THICKNESS**

Approximately 1.2 mil dry film thickness



**DRY TIMES**

**AIR DRYING**

Drying time at 68°F/20°C: 15-20 min. or max. 8 hrs. prior to Permacron® Base Coat Series 293/295  
 20-30 min. prior to Permahyd® Hi-TEC 480  
 2 hours prior to sanding

**LOW BAKE**

Drying time at 140°F/60°C metal temp.: 30 minutes

**WET SANDING**

Initial sanding: P320  
 Final sanding: P600 – 800

**RECOAT**

With Permacron® Base Coat Series 293/295 or Permahyd® Hi-TEC 480



**PHYSICAL PROPERTIES**

**Coating Category:** Primer  
 Max. VOC (AP): 662 g/l; 5.5 lbs/gal  
 Max. VOC (LE): 662 g/l; 5.5 lbs/gal  
 Avg. Gallon Weight: 1048.1 g/l; 8.75 lbs/gal  
 Avg. Weight % Volatiles: 63.2%  
 Avg. Weight % Water: 0.0%  
 Avg. Weight % Exempt Solvent: 0.0%  
 Avg. Volume % Water: 0.0%  
 Avg. Volume % Exempt Solvent: 0.0%

Theoretical Coverage @ 1 mil: 378.5 sq/ ft.  
 Theoretical Coverage @ Recommended Film Build: 252 sq/ ft.

**VOC REGULATED AREAS**

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.

**SAFETY AND HANDLING**

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.



Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties

Revised: June 2016

