



Permacron® Fine Putty 7715



GENERAL

DESCRIPTION

A one component putty based on a special acrylic resin combination that requires no additional components for drying. Permacron® Fine Putty 7715 has a neutral light beige color and is suitable for touching up prepared substrates or can also be applied on bare sheet metal. Permacron® Fine Putty 7715 spreads on very easily and pore-free and after a short drying time can be very easily sanded.

The products referenced herein may not be available for sale in your market. Please consult your distributor for product availability.



MIXING

COMPONENTS

Permacron® Fine Putty 7715

MIX RATIO

Ready-to-use

SPECIAL TIPS

1. Permacron® Fine Putty 7715 may not be applied over bare aluminum or galvanized panels and is also not suitable for use on plastic parts.
2. Minimum drying temperature for Permacron® Fine Putty 7715 is 59°F/15°C.



APPLICATION

SUBSTRATES

Steel

Original or old paintwork (except reversible substrates, Example: lacquer)
Permasolid® Primers/Surfacers.

SURFACE PREPARATION

- Degrease and sand.
- Before further treatment, clean all substrates thoroughly with Permaloid® Silicone Removers 7087 or 7010 Slow, Permahyd® Silicone Remover 7085, or Permahyd® Silicone Remover 7096.

APPLICATION

- Apply with a putty knife or razor blade in thin coats approximately 10 minutes apart.



DRY TIMES

AIR DRYING

Drying time at 68°F/20°C:

Approximately 30-60 minutes depending on film thickness

INFARED DRYING

Approximately 4-6 minutes



DRY SANDING

Sanding

P400 – 800

RECOAT

With Priomat® Primers and Primer/Surfacers, Permasolid® and Permahyd® Primers/Surfacers, Permacron® Base Coat Series 293/295, or Permahyd® Hi-TEC 480.



PHYSICAL PROPERTIES

Max. VOC (AP/LE): 398 g/l; 3.2 lbs/gal
 Avg. Gallon Weight: 1618 g/l; 13.6 lbs/gal
 Avg. Weight % Volatiles: 24.4%
 Avg. Weight % Water: 0.0%
 Avg. Weight % Exempt Solvent: 0.0%
 Avg. Volume % Water: 0.0%
 Avg. Volume % Exempt Solvent: 0.0%

VOC REGULATED AREAS

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.

SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties.

Revised: May 2016

