



Permasolid® Matte Clear Coat Additive 8092



GENERAL

DESCRIPTION

A low VOC (250 g/l), flexible clear coat additive designed to meet all OEM lower gloss requirements. It is compliant in the most stringently regulated areas and is suitable for both flexible and rigid repairs.

The products referenced herein may not be available for sale in your market. Please consult your distributor for product availability.



MIXING

COMPONENTS

Permasolid® Matte Clear Coat Additive 8092

PERMASOLID CLEAR COAT

Permasolid® HS Clear Coat 8035

PERMASOLID VHS HARDENERS

Permasolid® VHS Hardener 3230 Medium or
Permasolid® VHS Hardener 3240 Slow

For optimum hardener selection, refer to TDS # 061 or 3220-3245.

OPTIONAL COMPONENTS

REDUCERS

Permacron® Reducer 3363 Medium or
Permacron® Reducer 3365 Slow

For optimum reducer selection, refer to TDS # 780.0.

Or

PERMASOLID CLEAR COAT

Permasolid® Low VOC Clear Coat 8098

PERMASOLID LOW VOC HARDENERS

Permasolid® Low VOC Hardener 3194 Medium or
Permasolid® Low VOC Hardener 3196 Slow

For optimum hardener selection, refer to TDS # 062.

OPTIONAL COMPONENTS

REDUCERS

Permasolid® Reducer 3394 Medium

For optimum reducer selection, refer to TDS # 780.0.

Mix before application only. Do not pre-mix. Permasolid® Matte Clear Coat Additive 8092 may be mixed at different ratios to achieve varying levels of gloss. The following is only an approximate guide. Check gloss level with a spray out prior to applying on vehicle. See Special Tips below.



APPLICATION VISCOSITY

16-17 seconds at 68°F/20°C, DIN 4

POT LIFE

Approximately 0.5-1 hour at 68°F/20°C when ready to spray.

SPECIAL TIPS

- For additional recommendations, see TDS Permasolid® Matte Clear Coat Additive 8092 for Small Parts.
- Excellent for under hood matte finishes.
- Permasolid® Elastic Additive 9050 is not necessary when using Permasolid® Matte Clear Coat Additive 8092.
- Permasolid® Matte Clear Coat Additive 8092 must be mixed with a clear coat prior to use.
- The use of slow hardeners and reducer will aid in providing a uniform appearance.
- Spraying without reducer helps to create a more uniform gloss level.
- Actual gloss level also depends on basecoat color, hardener used, film thickness, and drying method.
- Spray out and verify gloss level prior to application.
- Shake well before use. Do not agitate on mix machine.
- Do not leave open, reseal immediately after pouring.
- Pre-strain the matte clear coat with a 125 micron filter before each use.
- For accurate mixing, use scale – see Mixing Tables above or use ColorNet®.
- Once mixed, the ready-to-spray matte clear coat should be applied immediately. If the mixed product is left in the mixing cup or spray gun cup for more than 15 minutes, it must be stirred again before use.
- For optimal appearance, apply 1½ coats of Permasolid® Clear Coat over the entire repair area and after a full bake or air drying overnight, sand the area with P1000-P2000 prior to applying the matte clear coat.
- Spray using a gun distance of 8 to 10 inches with 75% overlap. This helps create a more uniform gloss level.
- It is not possible to polish dust inclusions, therefore, cleanliness during the entire refinish process is very important.
- Do not attempt to polish the finish or the matte effect will be lost.
- Special care should be taken with the matte finish. For best results, follow the OEM Manufacturer’s care and maintenance recommendations.



APPLICATION

SUBSTRATES

Permacron® Base Coat Series 293/295
 Permahyd® Hi-TEC 480
 Fully cured OEM or existing topcoat (non-reversible)

SPRAYGUN SETUP

HVLP	1.3-1.5mm
Approved Transfer Efficiency	1.3-1.4mm

Please refer to gun manufacturer and local legislation for proper spray pressure recommendations.

APPLICATION

- Apply 2 coats with intermediate flash-off between coats.
- 5-15 minutes with US National Rule Clear Coats (until matte).
- 3-5 minutes with Low VOC Clear Coats (until matte).
- For additional details, see Special Tips above.

RECOMMENDED FILM THICKNESS

2.0-2.5 mil dry film thickness



DRY TIMES

LOW BAKE

Flash-off time Approx. 15 minutes
 Drying time at target metal temperature: 45 minutes at 140°F/60°C

RECOAT/RE-REPAIR

May be recoated any time after the bake cycle. If recoating after 24 hours scuff sand with 1200-1500 grit



PHYSICAL PROPERTIES

Coating Category: Clear Coating (8035 / HS Hardeners 5-10% gloss)

Max. VOC (AP): 336 g/l; 2.8 lbs/gal
 Max. VOC (LE): 443 g/l; 3.7 lbs/gal
 Avg. Gallon Weight: 1086.7 g/l; 9.07 lbs/gal
 Avg. Weight % Volatiles: 59.3%
 Avg. Weight % Water: 0.0%
 Avg. Weight % Exempt Solvent: 28.0%
 Avg. Volume % Water: 0.0%
 Avg. Volume % Exempt Solvent: 24.3%

Theoretical Coverage: 600.6 sq. ft. @ 1 mil
 Theoretical Coverage @ Recommended Film Build: 240–300 sq. f

Coating Category: Clear Coating (8035 / VHS Hardeners 5-10% gloss)

Max. VOC (AP): 336 g/l; 2.8 lbs/gal
 Max. VOC (LE): 443 g/l; 3.7 lbs/gal
 Avg. Gallon Weight: 1088.9 g/l; 9.09 lbs/gal
 Avg. Weight % Volatiles: 58.6%
 Avg. Weight % Water: 0.0%
 Avg. Weight % Exempt Solvent: 26.8%
 Avg. Volume % Water: 0.0%
 Avg. Volume % Exempt Solvent: 24.4%

Theoretical Coverage: 606.1 sq. ft. @ 1 mil
 Theoretical Coverage @ Recommended Film Build: 242–303 sq. ft.

Coating Category: Clear Coating (8035 / VHS Hardeners Designo finish)

Max. VOC (AP): 348 g/l; 2.9 lbs/gal
 Max. VOC (LE): 443 g/l; 3.7 lbs/gal
 Avg. Gallon Weight: 1084.4 g/l; 9.05 lbs/gal
 Avg. Weight % Volatiles: 58.6%
 Avg. Weight % Water: 0.0%
 Avg. Weight % Exempt Solvent: 26.8%
 Avg. Volume % Water: 0.0%
 Avg. Volume % Exempt Solvent: 23.2%

Theoretical Coverage: 612.1 sq. ft. @ 1 mil
 Theoretical Coverage @ Recommended Film Build: 245–306 sq. ft.



Coating Category: Clear Coating (8035 / VHS Hardeners Frozen finish)

Max. VOC (AP): 360 g/l; 3.0 lbs/gal
Max. VOC (LE): 455 g/l; 3.8 lbs/gal
Avg. Gallon Weight: 1077.7 g/l; 8.99 lbs/gal
Avg. Weight % Volatiles: 57.9%
Avg. Weight % Water: 0.0%
Avg. Weight % Exempt Solvent: 25.0%
Avg. Volume % Water: 0.0%
Avg. Volume % Exempt Solvent: 21.5%

Theoretical Coverage: 620.8 sq. ft. @ 1 mil
Theoretical Coverage @ Recommended Film Build: 248–310 sq. ft.

Coating Category: Clear Coating (8035 / VHS Hardeners 40-45% gloss)

Max. VOC (AP): 360 g/l; 3.0 lbs/gal
Max. VOC (LE): 455 g/l; 3.8 lbs/gal
Avg. Gallon Weight: 1071.7 g/l; 8.94 lbs/gal
Avg. Weight % Volatiles: 57.3%
Avg. Weight % Water: 0.0%
Avg. Weight % Exempt Solvent: 23.4%
Avg. Volume % Water: 0.0%
Avg. Volume % Exempt Solvent: 20.0%

Theoretical Coverage: 628.7 sq. ft. @ 1 mil
Theoretical Coverage @ Recommended Film Build: 252–314 sq. ft.

Coating Category: Clear Coating (8098 / Low VOC Hardeners 5-10% gloss)

Max. VOC (AP): 228 g/l; 1.9 lbs/gal
Max. VOC (LE): 324 g/l; 2.7 lbs/gal
Avg. Gallon Weight: 1118.2 g/l; 9.33 lbs/gal
Avg. Weight % Volatiles: 56.1%
Avg. Weight % Water: 0.0%
Avg. Weight % Exempt Solvent: 32.9%
Avg. Volume % Water: 0.0%
Avg. Volume % Exempt Solvent: 29.1%

Theoretical Coverage: 663.5 sq. ft. @ 1 mil
Theoretical Coverage @ Recommended Film Build: 265– 332 sq. ft.

Coating Category: Clear Coating (8098 / Low VOC Hardeners Designo Finish)

Max. VOC (AP): 228 g/l; 1.9 lbs/gal
Max. VOC (LE): 324 g/l; 2.7 lbs/gal
Avg. Gallon Weight: 1116.8 g/l; 9.32 lbs/gal
Avg. Weight % Volatiles: 55.9%
Avg. Weight % Water: 0.0%
Avg. Weight % Exempt Solvent: 32.6%
Avg. Volume % Water: 0.0%
Avg. Volume % Exempt Solvent: 28.8%

Theoretical Coverage: 665.1 sq. ft. @ 1 mil
Theoretical Coverage @ Recommended Film Build: 266–333 sq. ft.

Coating Category: Clear Coating (8098 / Low VOC Hardeners Frozen Finish)

Max. VOC (AP): 228 g/l; 1.9 lbs/gal
Max. VOC (LE): 324 g/l; 2.7 lbs/gal
Avg. Gallon Weight: 1115.4 g/l; 9.31 lbs/gal
Avg. Weight % Volatiles: 55.8%



Avg. Weight % Water: 0.0%
Avg. Weight % Exempt Solvent: 32.3%
Avg. Volume % Water: 0.0%
Avg. Volume % Exempt Solvent: 28.5%

Theoretical Coverage: 667.5 sq. ft. @ 1 mil
Theoretical Coverage @ Recommended Film Build: 267–334 sq. ft.

Coating Category: Clear Coating (8098 / Low VOC Hardeners 40-45% gloss)

Max. VOC (AP): 228 g/l; 1.9 lbs/gal
Max. VOC (LE): 324 g/l; 2.7 lbs/gal
Avg. Gallon Weight: 1113.7 g/l; 9.29 lbs/gal
Avg. Weight % Volatiles: 55.7%
Avg. Weight % Water: 0.0%
Avg. Weight % Exempt Solvent: 32.0%
Avg. Volume % Water: 0.0%
Avg. Volume % Exempt Solvent: 28.1%

Theoretical Coverage: 670.5 sq. ft. @ 1 mil
Theoretical Coverage @ Recommended Film Build: 268–335 sq. ft.

VOC REGULATED AREAS

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.

SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Any analytical results set forth herein do not constitute a warranty of specific product features or of the product's suitability for a specific purpose. All products are sold pursuant to our general conditions of sale. We hereby disclaim all warranties and representations, express or implied, with respect to this product, including any warranty of merchantability or fitness for a particular purpose. This product is protected by patent law, trademark law, copyright law, international treaties and/or other applicable law. All rights reserved. Unauthorized sale, manufacturing or use may result in civil and criminal penalties.

Revised: July 2022