

NUW312X

Amarium™ Pre-Catalyzed White Lacquers-275 VOC HAPs Free

Date: August 31, 2017 (supersedes all previous revisions)



GENERAL INFORMATION

Axalta's Amarium™ Pre-catalyzed White Lacquers are highly versatile premium quality finishes formulated to offer excellent durability combined with outstanding ease of use. They offer excellent mar, solvent, and chemical resistance. When properly applied with their companion undercoat, the film properties of this system provide a tough, durable finish that passes all KCMA performance standards. These products can also be used as a white/pastel base and the containers are short filled for easy tinting. This product is designed for professional application only. For Wood Substrates Only.



1. PRODUCTS

- NUW3126 – Semi- Gloss
- NUW3122 - Satin



2. MIXING RATIO

- All products should be stirred well before use and, for best results, continuously agitated while in use.



3. SHELF LIFE @ 77°F (25°C)

- 9 months



4. CLEAN UP

- Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal.



5. ADDITIVES



6. SURFACE PREPARATION

- Surface must be clean and dust free with a moisture content of 6-8% prior to finishing. Remove all dust, dirt, wax and wood marks. Proper sanding and preparation of the wood is critical to achieving consistent results.
- On new wood, finish sand surface with 150-180 grit sandpaper
- On previously finished wood, remove all old paint or varnish and follow new wood procedure.



7. COMPANION PRODUCTS

- NUW3120 – Amarium™ White Pre-Catalyzed Lacquer Undercoat -275 VOC



8. TECH NOTES

- No thinning is recommended.



9. SUBSTRATES

- Commonly used furniture and cabinetry woods
- MDF/HDF

NOTE: Not to be used on exterior applications



10. APPLICATION

- Apply at a rate of 3-4 wet mils per coat. Sand between coats with 240-320 grit, no fill sandpaper. This finish must be sanded between coats for proper adhesion. DO NOT APPLY more than three coats at 3-4 wet mils per coat when used in conjunction with the undercoat. Maximum film thickness of the total coating system MUST NOT EXCEED 4 dry mils.



11. FLASH / DRY TIMES

AIR DRY @ 77°F (25°C)

Dry to touch	15-20 Minutes
Flash between coats	30 - 45 Minutes
To Stack	16 - 24 Hours



12. FORCE DRY

Flash	8 – 10 Minutes
Bake	15 Minutes @ 125°F
Cool Down	10 Minutes ambient
Stack	2 hours after cool down



13. GUN SET UP

Gravity Feed	1.4 mm - 1.8 mm
Siphon Feed	1.4 mm - 1.8 mm
Airless	10 – 15 thousandths
Air-Assisted Airless	11 – 15 thousandths

AIR PRESSURES

Gravity Feed	30-35 psi (2.0-2.4 bar)
Siphon Feed	35-40 psi (2.4-2.8 bar)
Air-Assisted Airless	5-10 psi (0.3-0.7 bar)
See spray gun manufacturer data for more information	



14. PHYSICAL DATA

Viscosity	17-21 sec. EZ Zahn 2
Weight Solids %	31.46-31.51%
Volume Solids %	19.37-19.61%
Actual VOC	0.58-0.61lbs/gal of Product
VOC Ratio (lb.voc/lb.solids)	0.22-0.23lb VOC/lb solid
Regulatory VOC (less water and exempt solvents)	246.89-249.01 g/l
Weight Per Gallon	8.5-8.52 lbs/gal
Flash Point	50°F Closed Cup
Theoretical Coverage	310-314 ft/gal @ 1 mil dry
VHAP (lb.HAP/lb.solids)	0.0lb VHAP/lb solid
Photochemically Reactive	No
Coating Category	Clear

NUW312X

Amarium™ Pre-Catalyzed White Lacquers-275 VOC HAPs Free

Date: August 31, 2017 (supersedes all previous revisions)



Application Notes:

General:

Always pre-test the system on your substrate to verify suitability of the application.

First-Prime the wood with NUW3120 Amarium™ Pre-Catalyzed White lacquer Undercoat-275 VOC for best results.

Tinting: This product can be tinted with approved, high quality industrial colorants. (Check with your Axalta Distributor approved colorants). **NEVER** tint with colorants that contain glycol. Maximum tint load is 4 oz per gallon (3% by volume). Colorants must be mixed in completely with mechanical agitation before use. Apply by spray only, using Conventional Air, HVLP, Airless, or Air Assisted Airless equipment. Apply at a rate of 3-4 wet mils per coat. Sand between coats with 240-320 grit, no fill sandpaper. Remove sanding dust before applying the next coat. This finish must be sanded between coats for proper adhesion.

DO NOT APPLY more than three coats at 3-4 wet mils per coat when used in conjunction with the undercoat. Maximum film thickness of the total coating system MUST NOT EXCEED 4 dry mils.

Drying Times:

Dry to Touch: 15-20 minutes

Dry to sand and recoat: 30-45 minutes (depending on ambient conditions).

Do not apply if the material or substrate temperature is below 55°F.

This product is best applied when surface and air temperatures are between 55°-90° F (~12-32°C) and when relative humidity is below 50% during application and drying time.

Clean Up:

Refer to your local regulations for compliance requirements for cleaning solvents. Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal.

Precautions:

These products are recommended for professional application and are designed for interior use only. Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and to avoid potential need for costly refinishing. Axalta Industrial Wood Coatings are designed to protect and enhance the natural beauty of wood, but cannot eliminate natural discoloration or deterioration of wood as it ages.

Additional notes:

Do not mix with other finishing systems or deviate from these finishing recommendations. Axalta will not be held liable for finish failures resulting from the mixing of products or deviations from finishing recommendations.

Storage:

Store in a cool, dry place. Close all containers after use. Do not store near heat or sparks. Spills should be cleaned up with non-sparking tools. See the product MSDS for complete safety information.

Warning:

Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and avoid potential need for costly refinishing. All dry times listed are as tested under ideal indoor environmental conditions of 78°F (26°C) with relative humidity not exceeding 50%. These products are recommended for use under temperature conditions of 60-100°F (16-38°C) and when relative humidity is below 50% during application and drying time. Low temperatures, poor air circulation or high humidity will extend dry times. **Axalta strongly recommends against use of these products if temperatures of air, material, or surface to be coated are below 60°F (16°C) or below the dew point. Abnormal conditions of temperature or humidity may adversely affect product performance.** Please contact your authorized Axalta Industrial Wood Coatings distributor for additional product use recommendations and finishing guidance.