

NRS1400

Luster Lac™ Professional High Build Lacquer Sealer – 680VOC



Date: August 31, 2017 (supersedes all previous revisions)



GENERAL INFORMATION

Axalta's LUSTER LAC™ Professional Lacquer Sealer is a high quality, versatile lacquer sealer formulated for excellent performance on a variety of substrates used in interior wood finishing. It is a very fast drying, easy to apply sealer, with excellent flow and build properties. It is easy to touch-up, recoat and repair and has excellent sanding properties. This product is designed for professional application only. For Wood Substrates Only.



1. PRODUCTS

- NRS1400



2. MIXING RATIO

- Stir thoroughly, do not shake. No thinning is recommended.



3. SHELF LIFE @ 77°F (25°C)

- 24 months



4. CLEAN UP

- Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal.



5. ADDITIVES



6. SURFACE PREPARATION

- Surface must be clean and dust free with a moisture content of 6-8% prior to finishing. Remove all dust, dirt, wax and wood marks. Proper sanding and preparation of the wood is critical to achieving consistent results.
- On new wood, finish sand surface with 150-180 grit sandpaper
- On previously finished wood, remove all old paint or varnish and follow new wood procedure.



7. COMPANION PRODUCTS

- NRF140X Series topcoats
- Graintone Plus™ stain system



8. TECH NOTES



9. SUBSTRATES

- Commonly used furniture and cabinetry woods
- MDF/HDF

NOTE: Not to be used on exterior applications



10. APPLICATION

- Generally, only one coat is needed. DO NOT APPLY more than two coats at 3-4 wet mils per coat. Topcoat with NRF140X series Luster Lac™ Professional Lacquers. Maximum film thickness of the total coating system MUST NOT EXCEED 4 dry mils.



11. FLASH / DRY TIMES

AIR DRY @ 77°F (25°C)

Dry to touch	10-15 Minutes
Sand/Recoat	20-30 Minutes
To Stack	16-24 Hours

NRS1400

Luster Lac™ Professional High Build Lacquer Sealer – 680VOC



Date: August 31, 2017 (supersedes all previous revisions)

12. FORCE DRY

Flash	8-10 Minutes
Bake	5 Minutes @ 125°F
Cool Down	10 Minutes ambient
Stack	2 hours after cool down

13. GUN SET UP

Gravity Feed	1.8 mm – 2.2 mm
Siphon Feed	1.8 mm – 2.0 mm
Airless	10 – 15 thousandths
Air-Assisted Airless	11 – 15 thousandths

AIR PRESSURES

Gravity Feed	30-35 psi (2.0-2.4 bar)
Siphon Feed	35-40 psi (2.4-2.8 bar)
Air-Assisted Airless	5-10 psi (0.3-0.7 bar)
See spray gun manufacturer data for more information	

Application Notes:

General:

Always pre-test the system on your substrate to verify suitability of the application.

Apply by spray only, using Conventional Air, HVLP, Airless, or Air Assisted Airless equipment. Apply at a rate of 3-4 wet mils per coat. Sand between coats with 240-320 grit, no fill sandpaper. Remove sanding dust before applying the next coat.

Generally, only one coat is needed. DO NOT APPLY more than two coats at 3-4 wet mils per coat. Topcoat with NRF140X series Luster Lac™ Professional Lacquers. Maximum film thickness of the total coating system MUST NOT EXCEED 4 dry mils.

Drying Time:

Dry to touch: 10-15 minutes

Dry to sand and recoat: 20-30 minutes (depending on ambient conditions).

Do not apply if the material or substrate temperature is below 55°F.

This product is best applied when surface and air temperatures are between 55°-90° F (~12-32°C) and when relative humidity is below 50% during application and drying time.

Clean Up:

Refer to your local regulations for compliance requirements for cleaning solvents. Dispose of dirty solvent and cleaning rags in a safe and compliant manner. Solvent or lacquer soaked rags should be stored in water-filled, closed containers prior to disposal.



14. PHYSICAL DATA

Viscosity	55-57 KU Stormer
Weight Solids %	20.30%
Volume Solids %	14.32%
Actual VOC	4.49lbs/gal of Product
VOC Ratio (lb.voc/lb.solids)	3.07lb VOC/lb solid
Regulatory VOC (less water and exempt solvents)	664.95 g/l
Weight Per Gallon	7.21 lbs/gal
Flash Point	27°F Closed Cup
Theoretical Coverage	229.77 ft/gal @ 1 mil dry
VHAP (lb.HAP/lb.solids)	0.0lb VHAP/lb solid
Photochemically Reactive	No
Coating Category	clear



Precautions:

These products are recommended for professional application and are designed for interior use only. Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and to avoid potential need for costly refinishing. Axalta Industrial Wood Coatings products are designed to protect and enhance the natural beauty of wood, but cannot eliminate natural discoloration or deterioration of wood as it ages.

Additional notes:

Do not mix with other finishing systems or deviate from these finishing recommendations. Axalta will not be held liable for finish failures resulting from the mixing of products or deviations from finishing recommendations.

Storage:

Store in a cool, dry place. Close all containers after use. Do not store near heat or sparks. Spills should be cleaned up with non-sparking tools. See the product MSDS for complete safety information.

Warning:

Always pre-test the system on your substrate and under your line conditions to verify suitability to the application and avoid potential need for costly refinishing. All dry times listed are as tested under ideal indoor environmental conditions of 78°F (26°C) with relative humidity not exceeding 50%. These products are recommended for use under temperature conditions of 55°-90° F (~12-32°C) and when relative humidity is below 50% during application and drying time. Low temperatures, poor air circulation or high humidity will extend dry times. **Axalta strongly recommends against use of these products if temperatures of air, material, or surface to be coated are below 55°F (12°C) or below the dew point. Abnormal conditions of temperature or humidity may adversely affect product performance.** Please contact your authorized Axalta Industrial Wood Coatings distributor for additional product use recommendations and finishing

NRS1400

Luster Lac™ Professional High Build Lacquer Sealer – 680VOC



Date: August 31, 2017 (supersedes all previous revisions)

guidance.