


# Nason®XL 431-22 DTM Grey Primer





# GENERAL

#### DESCRIPTION

NasonXL 431-22 is a 4.8 lb/gal (575 g/l) VOC compliant, 2K urethane, direct-to-metal primer-filler designed to provide high build, and an exceptionally free-sanding film without shrinkage or sand scratch swelling.

#### **COMPATIBLE SUBSTRATES**

Properly cleaned and prepared steel, aluminum and galvanized metal. Properly sanded and prepared OEM finishes, cured paint, cured body filler and properly sanded fiberglass. Properly prepared rigid plastic.

Use Axalta VS3000 Etch Primer over galvanized steel is an industry best practice.

The products referenced herein may not be sold in your market. Please consult your distributor for product availability.

#### COLOR

431-22 Grey



# COMPONENTS

MIXING

Mix 4 parts NasonXL 431-22 DTM Grey Primer to 1 part NasonXL 445-10 Super Fast Activator, 445-11 Fast Activator, or 445-12 Standard Activator. Spray viscosity 11-13 seconds in Zahn #3 @ 77°F (25°C).

#### Component

NasonXL 431-22 DTM Grey Primer NasonXL National Rule Activator (445-10 Super Fast, 445-11 Fast, 445-12 Standard) Volume 4 1



#### Package Size

1 gallon (3.785 liters)

INITIAL APPLICATION VISCOSITY Zahn #3 Viscosity 11-13 seconds

POT LIFE 1 Hour @75°F (24°C)



# APPLICATION

#### **APPLICATION EQUIPMENT**

HVLP Gravity	1.7 - 1.9 mm	7 - 9 PSI	at the cap
High Efficiency	1.7 - 1.9 mm	21 - 28 PSI	at the gauge

NOTE: Refer to spray gun manufacturer for further information regarding HVLP Inlet Pressures

#### SURFACE PREPARATION

Remove dust or oxidation prior to applying primer by media blasting, grinding or sanding. Be certain all surfaces are free of waxes, oils, grease or other contaminants.

Over galvanized steel, an industry best practice is to use an etch primer such as Axalta VS3000 Etch Primer.

NOTE: Do not use over lacquer primer, lacquer finishes, or uncured substrates.

#### **APPLICATION**

Apply in single wet coats, allowing 5-10 minute flash at 75°F (24°C) between coats. For standard fill: We suggest 2 coats maximum. If 3 coats are applied, allow for overnight drying. 2 mils minimum final film is need to provide good corrosion protection.



# DRY TIMES

AIR DRY 1 Hour @75°F (24°C) per 1-2 coats

Overnight for high build 3 coats

Bake 20 Minutues @140°F (60°C)

INFARED SHORT WAVE 20 Minutes full power @36"





### **PHYSICAL PROPERTIES**

Recommended Film Thickness Recommended coats Theoretical Coverage: Flash Point: ± 50 microns / 2.0 mils per coat, dry film build 1-3 (x1) 645 ft<sup>2</sup> (50.4 m<sup>2</sup>) at 1 mil See SDS

#### **STORAGE CONDITIONS**

Store in a dry, well ventilated area. Storage temperatures should be between  $-30^{\circ}F(-34^{\circ}C)$  and  $120^{\circ}F(48^{\circ}C)$ .

# **VOC REGULATED AREAS**

All Values Ready To Spray

Standard Reduction (4:1) 575g/L (4.6 lbs./gal)

Max. VOC (LE)

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.

# SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and SDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Revised: April 2023

In the United States: 1.855.6.AXALTA NasonXL.us

