


Nason®XL 431-31 2.1 VOC Primer Surfacer





GENERAL

DESCRIPTION

NasonXL 431-31 2.1 VOC Primer Surfacer is a high-build, two component primer filler (surfacer) for automotive refinishing and new bodywork. 431-31 is designed to provide an excellent substrate for all refinishing with excellent gloss hold out.

COMPATIBLE SUBSTRATES

Thoroughly sanded OEM finishes adjoining metal. Thoroughly sanded and cured paint adjoining metal. Properly cleaned and prepared steel, aluminum, galvanized steel following an etch primer. Properly prepared semi-rigid plastic and fiberglass.

The products referenced herein may not be sold in your market. Please consult your distributor for product availability.

A+B+C MIXING

COMPONENTS

5 parts NasonXL 431-31 2.1 VOC Primer Surfacer to 1 part NasonXL Low VOC Activator. Reduce with 1 part NasonXL 437-00 Low VOC Reducer. Spray viscosity of 14-17 secs with Zahn #3 @ 77°F (25°C).

Maximum RFU (ready for use) VOC 2.1 lbs/gal.

Component NasonXL 431-31 2.1 VOC Primer Surfacer	Volume 5
NasonXL Low VOC Activator	
(435-14 Standard or 435-15 Slow)	1
NasonXL 437-00 Low VOC Reducer	1



Package Sizes

- 1 gallon (3.785 liters)
- 1 quart (0.95 liters)

INITIAL APPLICATION VISCOSITY Zahn #3 Viscosity 14-17 seconds.



APPLICATION

APPLICATION EQUIPMENT

HVLP Gravity 1.7 -1.9 mm 6-8 PSI High Efficiency 1.7 -1.9 mm 17-19 PSI at the cap at the gauge

Note: Refer to spray gun manufacturer for further information regarding HVLP Inlet Pressures

SURFACE PREPARATION

Degrease then sand with P180-P320 grit sandpaper. Abrade steel with P80-P180 grit sandpaper. Dry sand P360-P400 grit sandpaper. Existing surfaces (featheredge); P180-P400 grit sandpaper. Large areas of bare metal should be etch primed prior to application of 431-31 Primer Surfacer.

APPLICATION

Shake or stir product before use. Be sure that primer is thoroughly mixed. Apply 1-3 single coats depending on desired film build. Allow 5-10 minute flash off between coats.



DRY TIMES

AIR DRY To Sand Bake

1 Hour @ 77°F (25°C) per coat 30 Minutes @140°F (60°C) metal temperature

Infrared Short Wave

15 Minutes full power @36"



PHYSICAL PROPERTIES

Recommended Film Thickness Theoretical Coverage: at 1 mil Recommended Coats Flash Point: 1.6 to 2.0 mil in 1 coat 621 ft² /RTS Gal(15.3 m² /RTS L) 1-3 (x1) See SDS

STORAGE CONDITIONS

Store in a dry, well ventilated area. Storage temperatures should be between -30°F (-34°C) and 120°F (48°C).



VOC REGULATED AREAS

All Values Ready To Spray

	Standard Reduction (5:1:1)
Max. VOC (LE)	232 g/L (1.9 lbs./gal)
Max. VOC (AP)	122 g/L (1.0 lbs./gal)
Avg. Gal. Wt.:	1470 g/L (12.27 lbs./gal)
Avg. Wt.% Volatiles:	46.8%
Avg. Wt.% Exempt Solvent:	38.5%
Avg. Wt.% Water:	0.0%
Avg. Vol.% Exempt Solvent:	47.7%
Avg. Vol.% Water:	0.0%

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.

SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and SDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Revised: January 2023

In the United States: 1.855.6.AXALTA NasonXL.us