



Corlar® 2.1 PR™ High Solids Epoxy Mastic Primer



GENERAL

DESCRIPTION

A high build epoxy mastic, two-package, VOC conforming product (2.1 lbs/gal) based on Axalta amido amine modified polyamide epoxy technology. The resulting coating is formulated to be highly durable and to deliver outstanding corrosion and chemical resistance.

SUGGESTED USES

As a high performance primer or intermediate coat on carbon steel, galvanized steel, stainless steel, aluminum, concrete, concrete block and wood where:

- Rusted, hand or power-tool cleaned surfaces must be protected.
- Single coat applications up to 10 mils dry film thickness are required.
- Application will be made over damp surfaces and/or under conditions of high relative humidity.
- Excellent resistance to chemical and/or marine environments is required.
- Outstanding abrasion resistance and edge protection are required.
- Application by brush and roller, in addition to spraying, may be necessary.
- Application must be made at temperatures as low as 35°F.
- No induction time and long pot life will improve productivity.

Corlar 2.1 PR may also be used as a high performance tank lining primer under Corlar 2.1 ST™ on carbon steel or concrete for immersion service in near neutral pH water, fresh water, or saltwater. Corlar 2.1 PR is not recommended for use with potable water. Contact your Axalta representative for specific immersion service recommendations and procedures.

Corlar 2.1 PR is primarily designed for corrosion protection. Corlar 2.1 PR will chalk upon exposure to sunlight. If gloss, color retention and color stability are important, Corlar 2.1 PR should be topcoated with Imron® Industrial Strength, Imron 2.1 HG™ + or Imron 3.5 HG™ + or other appropriate topcoat. In high temperature applications, some yellowing may occur.

COMPATIBILITY WITH OTHER COATINGS

- Corlar 2.1 PR is highly compatible with most coating types. It may be used over most aged and hard cured coatings in good condition. Testing for lifting, bubbling and adhesion is recommended to assure compatibility with unknown coatings. Contact your Axalta representative for specific recommendations.

NOT RECOMMENDED FOR

- Immersion service in potable water, chemicals or hydrocarbons
- Extreme exposure without topcoat

RECOMMENDATIONS FOR IMMERSION SERVICE

Corlar 2.1 PR when applied in multiple coats (at least 2) at 10-12 mil DFT is recommended for immersion service in near neutral, fresh or saltwater exposures. It is not recommended for use with potable water. It may be used for fire water towers, ballast tanks, clarifiers, wastewater treatment plants, offshore structures, pier pilings and supports and other areas where a high level of water resistance is required. Do not roll for immersion applications. Spray apply only.

The products referenced herein may not be sold in your market. Please consult your distributor for product availability.



PERFORMANCE PROPERTIES

Abrasion & Mechanical	Excellent
Alkalis	Excellent
Humidity	Excellent
Solvents	Excellent
Acids	Very Good
Salts	Excellent
Weather	Very Good (will chalk on exterior exposure)
Ammonia	Excellent

COLOR

Red oxide



MIXING

COMPONENTS

Corlar 2.1 PR – LF-71125™ Base	1 gallon container 100% Full (128 oz.)
Corlar VF-525™ Activator	1 gallon container 100% Full (128 oz.)

MIX RATIO

Component	Part by Vol.
Corlar 2.1 PR - LF-71125P Base	1
Corlar VF-525 Activator	1

ACTIVATION

Add 1 part Corlar VF-525 Activator to 1 part Corlar 2.1 PR (LF-71125P) base. Mix until thoroughly blended. You may begin painting immediately—there is no induction time.

Reduction

2-5% of Y-32035™ is required under normal conditions for airless spray. 7-10% of Y-32035 is the suggested level of thinning for conventional spray. For maximum pot life, reduce 15% by volume with Y-32035 or RT001P™. Use 10-15% T-8054™ Thinner in hot or windy conditions for spray application. Reduce 10-15% with RT001P Thinner when applying by roller or brush. If more reduction is required, consult your local Axalta representative.

For use in 2.08 VOC Restricted Areas: 10% T-1025™ must be added with constant mixing. Use without T-1025 or with any other thinner will result in VOC levels higher than 2.08 lbs/gal. At 15% reduction, reduced maximum film thickness will be obtained.

APPLICATION THINNERS

Normal Conditions	Y-32035
Hot or Windy Conditions	T-8054 (spray)
Brush or Roll	RT001P
For 2.08 VOC	T-1025

POT LIFE

8 hours @ 70°F to 90°F when reduced 15% by volume with Y-32035 or RT001P thinner.



APPLICATION

SURFACE PREPARATION

For atmospheric service, an SSPC-SP 6 Commercial Blast Cleaning is preferred for optimal performance. If not possible or practical, then Hand Tool Clean to an SSPC-SP 2 or Power Tool Clean to an SSPC-SP 3. For immersion service, an SSPC-SP 5 White Metal Blast is required.

APPLICATION CONDITIONS

Do not apply if material, substrate or ambient temperature is below 35°F (2°C) or above 100°F (38°C). For intermittent service temperatures above 250°F, do not topcoat.



ROLL APPLICATION

Manufacturer: Wooster® Pro/Doo-Z 1/2"- 3/4" nap

- Keep roll wet. Roll in one direction, rewet, then cross roll.
- Do not roll for immersion applications. Spray apply only.

BRUSH APPLICATION

Manufacturer: Wooster® China Bristle - 3"-4" brush

SPRAY APPLICATION

Manufacturers listed below are a guide. Others may be used. Changes in tip size or pressure may be required to achieve proper application.

Conventional Spray

	<u>Binks</u>	<u>DeVilbiss</u>	<u>SATA</u>
Spray Gun:	2001	JGA	K3RP
Fluid Nozzle:	63BSS	D (1.4)	1.1
Pot Pressure:			25
Atomizing Pressure			36
Air Cap:	63PB	765	

HVLP Spray

	<u>Binks</u>	<u>DeVilbiss</u>
Spray Gun:	Mach 1	GTi
Fluid Nozzle:	94 (1.4)	1.4
Air Cap:	97P	2000

Airless Spray

Pump: Graco Extreme 33:1
Airless Gun: Graco 208663
Fluid Hose: 3/8" x 50' max.
Tips: 413-621
Minimum pressure to avoid fingering: 2400 psi min.

Application Notes

- If using D fluid nozzle, minimize reduction to avoid runs and sags
- When applying over inorganic zinc primers, a mist coat is recommended for best results to minimize bubbling. Apply a mist coat and allow bubbles to break. Apply a full wet coat after mist coat.
- Under certain high humidity and low temperature conditions, an amine blush is possible. This blush should be removed before proceeding with next coat by wiping surface with an alcohol-based solvent.
- Epoxies chalk with extended exposure to sunlight. Lack of ventilation, incomplete mixing, mis-catalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause yellowing to occur.

Re-Coat

Recoating of Corlar 2.1 PR should be done as soon as possible after dry to touch, a minimum of 3-5 hours at 70°F, up to overnight. If you cannot recoat within 7 days up to 30 days, and you have not exposed the Corlar 2.1 PR to strong exterior sunlight and elevated temperatures over 100°F, you should water wash with a minimum of 1500 psi to remove any surface contamination. If you cannot recoat before 30 days and have exposed the Corlar 2.1 PR surfaces to exterior sunlight and elevated temperatures over 100°F, you should either:

Option 1: Water wash the surface with 1500 psi and apply 1-2 mils DFT tack-mist coat Corlar 2.1 PR over the existing Corlar 2.1 PR painted surface and topcoat within 3-5 hours up to overnight, or

Option 2: Water wash the surface with 1500 psi and abrasively brush-blast to an SSPC-SP7 (sweep-blast) and topcoat within 3-5 hours up to overnight.



CLEAN UP THINNERS
T-8054 or MEK



DRY TIMES

Cure Time At Recommended Thickness 5 mils DTF @ 50% RH

	<u>50°F (10°C)</u>	<u>70°F (21°C)</u>	<u>90°F (32°C)</u>
To Touch	3-4 hours	2-3 hours	1-2 hours
To Handle	8 hours	4 hours	2 hours
To Recoat	5 hours	3 hours	2 hours
Full Cure	14 Days	7 Days	4 Days



PHYSICAL PROPERTIES

Maximum Service Temperature Up to: 250°F Continuous
300°F Intermittent
100°F Immersion

Volume Solids 70% ± 2%
Weight Solids 83% ± 2%
Theoretical Coverage Per Gallon 1122 ft² @ 1 mil DFT
224 ft² @ 5 mils DFT
112 ft² @ 10 mils DFT

Material losses during mixing and application will vary and must be taken into consideration when estimating job requirements.

Weight Per Gallon 12.3 lbs./gal ± 0.2% | 5.64 kg. avg.
Shipping Weight (approximate) 1 gallon container: 14 (base) / 11 (activator);
5 gallon container: 64 (base) / 55 (activator)

Suggested Film Thickness:
Single Coat 5-8 mils - noncorrosive environment
10-12 mils - corrosive environment
Primer 3-8 mils
Mid Coat 4-6 mils
Immersion 10 - 12 mils

Application by brush and roller may require additional coats to achieve recommended films thickness.

Flash Point: Corlar 2.1 PR Bases > 100°F
Corlar VF-525 Activator < 73°F
Gloss: Satin Finish
Package Size: 1 & 5 gallon containers
Shelf Life: 12 months minimum

STORAGE CONDITIONS

Store in a dry, well-ventilated area. Storage conditions should be between -30°F (-34°C) and 120°F (48°C).

Corlar 2.1 PR may settle. Agitate before each use and intermittently while sitting in storage.

VOC REGULATIONS



VOC (Theoretical less water and exempt compounds).

<u>Condition</u>	<u>Thinner</u>	<u>%</u>	<u>VOC</u>	<u>VOC</u>
		<u>Max</u>	<u>(lbs/gal)*</u>	<u>(g/l)*</u>
Airless Normal	Y32035	2-5	2.3	276
Conventional	Y32035	7-10	2.5	300
Max. Pot Life	Y32035	15	2.7	324
	RT001P	15	2.8	336
Hot & Windy	T-8054	10-15	2.8	336
Brush & Roll	RT001P	10-15	2.8	336
Mixed	Unthinned		2.1	252
For 2.08 VOC Restricted Areas				
	T-1025	10	2.0	240

* Reported values at higher level of reduction (theoretical/avg. across colors.)

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.

ASTM INFORMATION

Test results are for a one-coat system of Corlar 2.1 PR . Properties for Corlar 2.1 PR are enhanced when used in conjunction with topcoats such as Imron polyurethane or applied at higher film builds. The results listed below are obtained when applying Corlar 2.1 PR to 5.3 mils DFT.

Paint System:	Corlar 2.1 PR	
Type Color:	Epoxy Red Oxide	
DFT:	5.3 mils	
Salt Fog (ASTM B117)	1000 hours	no rusting, no blisters
	2000 hours	no rusting, very few #2 blisters at the scribe
	3000 hours	no rusting, very few #2 blisters at the scribe, no undercutting at the scribe
Relative Humidity (ASTM D2247)	1000 hours	no rusting, no blisters
	2000 hours	no rusting, very few #2 blisters on the face of the panel
	3000 hours	no rusting, very few #2 blisters on the face of panel
Dry Heat (ASTM D2485)	250°F for 24 hours	no cracking, no blisters, very slight loss of adhesion, very slight discoloration
Electrical Resistance (ASTM D2457):	5.5X10 ¹⁷	
Adhesion (ASTM D4521 A2):	2038 psi	cohesive failure within coating
Cleveland Cond (ASTM D4585):	1000 hours	no rusting, no blisters, no delamination
UV Con (ASTM D4587)*	3000 hours	Gloss before exposure 29.5 Gloss after exposure 1.2
Impact (ASTM D2794):	1 inch pound	
Mandrel Bend (ASTM D522):	% Elongation - 0%	
Taber Abrasion (ASTM D4060):	weight loss in grams - 0.41	

*8 hour UV @ 50°C, 4 hour condensation @ 40°C, gloss readings @ 60°



SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable, and are intended for professional use by persons having skill and know-how at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendations, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.

Revised: January 2015

In the United States:
1.855.6.AXALTA
axalta.us

In Canada:
1.800.668.6945
axalta.ca

